

Technical Data Sheet

8823

Description/Application

A UL certified flame retardant, clear flexible PVC compound recommended for a maximum service temperature of 60C. Exhibits good migration resistance properties.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.24	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	83	ASTM D-2240
Tensile Strength, psi	2,600	ASTM D-638
Elongation, %	350	ASTM D-638
100% Modulus, psi	1,400	ASTM D-638

Recognitions and Approval

UL approved for 94Vo at 2.30 mm; 94V1 at 1.85 mm and 94V2 at 0.90 mm.

Recommended Stock Temperature 340 F

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 4/24/2003

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial