

5/25/23, 2:02 PM

Salesforce



HR-5009

Download as PDF



VINYL COMPOUNDS

HR-5009 Rigid

PRODUCT DESCRIPTION		
This rigid, non-phthalate compound is formulated to provide excellent high-flow properties for a variety of custom injection molding, pipe, and fitting applications. This fitting-grade compound is commonly used in large part, sprue/runner, and multi-cavity mold applications that require NSF 14/50/51/61 certifications. This compound possesses excellent regrind stability, color hold, and surface appearance.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.39	ASTM D-792
Mold Shrinkage 10 ⁻³ in/in	2-3	ASTM D-955
Flow Ratio (Distance/Wall Thickness, 390-400F)	170	AXIAL Method
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Yield Strength, psi	7300	ASTM D-638
Tensile Yield Strength, MPa	50	ASTM D-638
Tensile Modulus, psi	410000	ASTM D-638
Tensile Modulus, MPa	2827	ASTM D-638
Flexural Strength, psi	13000	ASTM D-790
Flexural Strength, MPa	90	ASTM D-790
Flexural Modulus, psi	420000	ASTM D-790
Flexural Modulus, MPa	2896	ASTM D-790
1/8" Notched Izod Impact ft-lbs/in at 23°C	1.1	ASTM D-256
1/8" Notched Izod Impact ft-lbs/in at -20°C	0.7	ASTM D-256
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Heat Deflection Temp °C at 66 psi/0.46 MPa	75	ASTM D-648
Heat Deflection Temp °C at 264 psi/1.8 MPa	71	ASTM D-648

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.