



CPE Grade
YUHWA HIDDEN C100

Description

- Application : CPE
- Features : Excellent flame resistance, Excellent weather resistance, Outstanding Electric Characteristics
- Uses : PVC Impact Strength Reforming Substance, Wire & Cable Jacket, Anti-corrosive Paint

Properties

Item	Value	Unit	Test Method
Melt Index (5kg / at 190°C)	0.55	g/10min	ASTM D1238
Density	0.953	g/cm ³	ASTM D1505
Bulk Density	0.41	g/cc	-
Avg. Particle Size	170	μm	Malvern PSD
Particle Distribution (~90 μm)	11	%	ASTM E11:61
Particle Distribution (90~150 μm)	40	%	ASTM E11:61
Particle Distribution (150~300 μm)	44	%	ASTM E11:61
Particle Distribution (300 μm~)	5	%	ASTM E11:61

• Above data are intended to serve as guides only, and are not sales specification limits.

Contact Info

14 Nov.2014

International Trade

TEL: 82-2-3706-0841~0849 FAX: 82-2-3706-0893~0894 e-mail: trade@kpicc.com

Technical Service

TEL: 82-80-010-1515, 82-2-2122-1532~1538 FAX: 82-2-2122-1519 e-mail: H15106@kpcc.co.kr