

KOREA PETROCHEMICAL IND.CO.,LTD

HDPE **P301E BL**
 print  close

Classification : HDPE Pipe grade
 Attributes : PE80, Creep Resistance, SCG, RCP, Color:Black
 Applications : Water Supply and Drain Pipes, Industrial Pipes

Documents & Certificates

Spec Sheet :  [kpic_spec_P301E-BL_en.pdf](#)
 MSDS :  [kpic_msds_P301E-BL_en.pdf](#)
 FDA :  [FDA Request](#)
 RoHS :  [kpic_RoHS_P301E BL_20080307.PDF](#)
 Certificates :  [LTHS\(Bodycote\)](#)  [RCP-S4 Test\(Bodycote\)](#)  [SCG The Notch Pipe Test \(Bodycote\)](#)  [Australlian WQC](#)  [WRAS](#)

Properties

ITEM (TERM)	VALUE	UNIT	TEST METHOD
Melt Index (190°C,2.16kg)	0.12	g/10min.	ASTM D1238
Density	0.958	g/cm ³	ASTM D1505
Tensile Strength at Yield	220	kgf/cm ²	ASTM D638
Elongation at Break	>600	%	ASTM D638
Flexural Modulus	8,500	kgf/cm ²	ASTM D790
Hardness (Rockwell)	30	R Scale	ASTM D785
Impact Strength (Izod with Notch)	>50	kgf cm/cm	ASTM D256
Environment Stress Cracking Resistance	>5,000	hr, F50	ASTM D1693
Melting Point	132	°C	ASTM D3418
Softening Point (Vicat)	122	°C	ASTM D1525
Oxidation Induction Time at 200°C	>40	min	ASTM D3895
Heat Deflection Temperature	60	°C	ASTM D648
Brittleness Temperature	< -70	°C	ASTM D746
Carbon Black Content	2.3	%	ISO 6964
Carbon Black Dispersion	<3	Grade	ISO 18553
The values given above should only be used as a guide and should not be considered as a specification or guarantee. The values are dependent on part geometry and fabrication conditions.			