


KOREA PETROCHEMICAL IND.CO.,LTD

U(V)HMWPE **U030**
 print
 close

Classification : U(V)HMWPE UHMWPE grade
 Attributes : Good property, Processibility balance
 Applications : Diverse Application (Compression Molding, Ram Extrusion. etc)

Documents & Certificates

Spec Sheet :  [kpic_spec_U030_en.pdf](#)
 MSDS :  [kpic_msds_U030_en\(1\).pdf](#)
 FDA :  [FDA Request](#)
 RoHS :  [kpic_RoHS_U030_20110908.PDF](#)

Properties

ITEM (TERM)	VALUE	UNIT	TEST METHOD
Average Mv (10^6 g/mol)	3	-	KPIC Method
Density	0.93	g/cm ³	ASTM D1505
Bulk Density	0.45	g/cm ³	ISO 60
Avg. Particle Size	120	μm	KPIC Method
Tensile Strength at Yield	>170	kg _f /cm ²	ASTM D638
Elongation at Break	>300	%	ASTM D638
Hardness (Rockwell)	63	Shore D	ASTM D785
Impact Strength (Izod with Notch)	No Break	kg _f cm/cm	ASTM D256
Abrasion Resistance	120	U050=100	ISO 15527
Melting Point	135	°C	ASTM D3418
Heat Deflection Temperature	79	°C	ASTM D648
The values given above should only be used as a guide and should not be considered as a specification or guarantee. The values are dependent on part geometry and fabrication conditions.			