

 KOREA PETROCHEMICAL IND.,CO.,LTD

General Homo PP 1088

 print  close

Classification : General Homo PP Film (IPP) grade
Attributes : IPP, General Purpose, Transparency
Applications : Food Packaging, Clothes Packaging, General Packaging

 Documents & Certificates

Spec Sheet :  kpic_spec_1088_en.pdf
MSDS :  kpic_msds_1088_en(1).pdf
FDA :  FDA Request
RoHS :  kpic_RoHS_1088_20130703.pdf

 Properties

ITEM (TERM)	VALUE	UNIT	TEST METHOD
Melt Index	10	g/10min.	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mold Shrinkage	1.1~2.0	%	KPIC Method
Water Absorption	<0.01	%	ASTM D570
Tensile Strength at Yield	360	kg _f /cm ²	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	16,000	kg _f /cm ²	ASTM D790
Hardness (Rockwell)	100	R Scale	ASTM D785
Impact Strength (Izod with Notch)	4	kg _f cm/cm	ASTM D256
Melting Point	163	°C	ASTM D3418
Softening Point (Vicat)	152	°C	ASTM D1525
Heat Deflection Temperature	110	°C	ASTM D648

The values given above should only be used as a guide and should not be considered as a specification or guarantee.

The values are dependent on part geometry and fabrication conditions.