

 KOREA PETROCHEMICAL IND.CO.,LTD

General Homo PP 5014L(2)

 print  close

Classification : General Homo PP Film (OPP) grade
Attributes : OPP, General Purpose, For Printing
Applications : Food Packaging, Clothes Packaing, General Packaging, Cigarette Packaging

 Documents & Certificates

Spec Sheet :  kplic_spec_5014L(2)_en.pdf
MSDS :  MSDS Request
FDA :  FDA Request

 Properties

ITEM (TERM)	VALUE	UNIT	TEST METHOD
Melt Index	2	g/10min.	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mold Shrinkage	1.0~2.0	%	KPIC Method
Water Absorption	<0.01	%	ASTM D570
Tensile Strength at Yield	360	kg _f /cm ²	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	16,000	kg _f /cm ²	ASTM D790
Hardness (Rockwell)	96	R Scale	ASTM D785
Impact Strength (Izod with Notch)	4	kg _f cm/cm	ASTM D256
Melting Point	162	°C	ASTM D3418
Softening Point (Vicat)	152	°C	ASTM D1525
Heat Deflection Temperature	105	°C	ASTM D648
The values given above should only be used as a guide and should not be considered as a specification or guarantee. The values are dependent on part geometry and fabrication conditions.			