

KOREA PETROCHEMICAL IND.CO.,LTD
HSPP Block Copolmer SB9108
 print
 close

Classification : HSPP Block Copolmer Injection grade
Attributes : High Gloss, Impact Resistance, High Stiffness, All Color 94HB
Applications : Electric and Electronic Product Parts, Automobile Parts, PP Compound Base Resin

Documents & Certificates

Spec Sheet :  [kpic_spec_SB9108_en.pdf](#)
MSDS :  [kpic_msds_SB9108_en\(1\).pdf](#)
FDA :  [FDA Request](#)
UL :  [KPIC_UL.pdf](#)
RoHS :  [kpic_RoHS_SB9108_20110825.PDF](#)

Properties

ITEM (TERM)	VALUE	UNIT	TEST METHOD
Melt Index	10	g/10min.	ASTM D1238
Density	0.91	g/cm ³	ASTM D1505
Mold Shrinkage	1.4~1.8	%	KPIC Method
Tensile Strength at Yield	300	kgf/cm ²	ASTM D638
Elongation at Break	>200	%	ASTM D638
Flexural Modulus	15,000	kgf/cm ²	ASTM D790
Hardness (Rockwell)	97	R Scale	ASTM D785
Impact Strength (Izod with Notch) 25°C	10	kgf cm/cm	ASTM D256
Impact Strength (Izod with Notch) -20°C	3	kgf cm/cm	ASTM D256
Melting Point	168	°C	ASTM D3418
Softening Point (Vicat)	152	°C	ASTM D1525
Heat Deflection Temperature	130	°C	ASTM D648
The values given above should only be used as a guide and should not be considered as a specification or guarantee. The values are dependent on part geometry and fabrication conditions.			